



Yes


mauser®  
SitzKultur




30




63




14




92




69



12



72



40

# Yes



## Stoffgruppe 2

**Zusammensetzung**  
100% Polyester FR

**Gewicht**  
490g/lf.d.M.±5%

**Breite**  
140cm

**Scheuerfestigkeit**  
60.000 Martindale Scheuertouren

**Feuersicherung**  
DIN 4102 B1

NFP 92-503 (bruleur electrique) M1

BS EN 1021 - 1:2006 (Zigarettestest) &  
BS EN 1021 - 2:2006 (Butananflammentest) in  
Kombination mit Schaumstoff B 3 normal brennbar  
mind. 23 kg/m<sup>3</sup> Raumgewicht Klassifizierung des  
Brandverhaltens des Polsterverbundes nach DIN  
66084 P-b

BS 5852 : 2006 Section 4 Ignition Source 5 in  
Kombination mit schwerentflammbarem Schaumstoff  
CMHR mind. 35 kg/m<sup>3</sup> Raumgewicht - Medium hazard

**Lichtechtheit**  
5 - 7 (ISO 105 - B02:2002)

**Reibechtheit**  
Nass: 4-5 Trocken: 4-5  
(ISO 105 - X12:2002)

**Reinigung**  
Festverspannte Bezüge: Absaugen,  
Trockenschäumreinigung  
Abnehmbare Bezüge: Chemische Reinigung, Waschen  
unter Pflegeleichtbedingungen bis 60 °C ohne  
Schleudern

**Farbabweichungen**  
Handelsübliche Farbabweichungen vorbehalten.

## Price Group 2

**Composition**  
100% Polyester FR

**Weight**  
490g/lin.m. ±5%

**Width**  
140cm

**Abrasion Resistance**  
60.000 Martindale cycles

**Flammability**  
DIN 4102 B1

NFP 92-503 (bruleur electrique) M1

BS EN 1021 - 1:2006 (cigarette) &  
BS EN 1021 - 2:2006 (butane flame) in combination  
with B3 foam flammable at minimum density of 23 kg/m<sup>3</sup>  
Upholstery flammability rating in accordance with DIN  
66084 P-b

BS 5852 : 2006 Section 4 Ignition Source 5 tested using  
non-flammable CMHR foam at minimum density of 35  
kg/m<sup>3</sup> - Medium Hazard

**Light Fastness**  
5 - 7 (ISO 105 - B02:2002)

**Fastness to Rubbing**  
Wet: 4-5 Dry: 4-5  
(ISO 105 - X12:2002)

**Maintenance**  
Fixed covers: Vacuum regularly. Clean with a dry foam.  
Removeable covers: Dry Clean. Machine wash up to  
60 °C, do not spin and do not tumble dry.

**Colour Matching**  
Batch to batch variations in shade may occur within  
commercial tolerances.

**mauser**  <sup>®</sup>  
Sitzkultur

Mauser Sitzkultur GmbH & Co. KG  
Erlengrund 3  
D-34477 Twistetal - Berndorf  
Fon. +49 (0) 5631 50514-0  
Fax +49 (0) 5631 50514-44  
www.mauser-sitzkultur.com

Zertifiziert nach DIN EN ISO 9001

